

Sicoflex ABS MZ340

Acrylonitrile Butadiene Styrene

Ravago Group

Message:

ABS, general purpose high flow

General Information			
Recycled Content	Yes		
Features	General Purpose		
	High Flow		
Uses	General Purpose		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	20	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	42.0	MPa	
Break	35.0	MPa	
Tensile Strain (Break)	28	%	ISO 527-2
Flexural Modulus	2700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	5.0	kJ/m ²	
23°C	9.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Annealed)	88.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	98.0	°C	ISO 306/A50
--	92.0	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating ¹			Internal Method
1.60 mm	HB		
3.20 mm	HB		
Glow Wire Flammability Index (2.00 mm)	650	°C	IEC 60695-2-12
NOTE			
1.	UL94 internally tested		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

