

3M™ Dyneon™ Fluoroelastomer FE 5622Q

Fluoroelastomer

3M Advanced Materials Division

Message:

3M™ Dyneon™ Fluoroelastomer FE 5622Q is a dipolymer made from hexafluoropropylene and vinylidene fluoride. FE 5622Q has an incorporated bisphenol cure system.

Special Features

Composition: dipolymer of vinylidene fluoride and hexafluoropropylene

Improved scorch resistance at high moulding temperatures

Excellent mould release

Process targets: injection, transfer and compression moulding, bonding and calendering

Proprietary incorporated cure technology

Clean running

Typical Applications

The development of 3M™ Dyneon™ Fluoroelastomer FE 5622Q targeted bonded shaft seal applications.

General Information	
Features	Good demoulding performance
Uses	Seals
	Bonding
Appearance	Opacity
	White-like
Forms	Thick sheet
Processing Method	Resin transfer molding
	Compression molding
	Calendering
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.80	g/cm ³	Internal method
Mooney Viscosity (ML 1+10, 121°C)	22	MU	Internal method
Fluorine Content	66	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	71		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain)	3.60	MPa	ASTM D412A
Tensile Strength ²	16.2	MPa	ASTM D412A
Tensile Elongation ³ (Break)	300	%	ASTM D412A
Compression Set			ASTM D1414
200°C, 70 hr ⁴	23	%	ASTM D1414
200°C, 70 hr ⁵	22	%	ASTM D1414

NOTE	
1.	D mould
2.	Die D
3.	D mould
4.	Post cured 16 hours @ 230°C
5.	Post cured 24 hours @ 260°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

