

HiFill® POM HO GF10

Acetal (POM) Homopolymer
Techmer Engineered Solutions

Message:

HiFill® POM HO GF10 is an Acetal (POM) Homopolymer product filled with glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

Flame Rated

Homopolymer

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Homopolymer		
Appearance	Colors Available		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.4	%	ASTM D955
Water Absorption (24 hr)	0.22	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	82		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	54.5	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	3480	MPa	ASTM D790
Flexural Strength	69.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	169	°C	
1.8 MPa, Unannealed	147	°C	
Melting Temperature	177	°C	
CLTE - Flow	4.7E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dielectric Strength ¹	16	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.57 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	93.3	°C	

Drying Time	2.0 to 3.0	hr
Rear Temperature	193 to 218	°C
Middle Temperature	193 to 218	°C
Front Temperature	193 to 218	°C
Processing (Melt) Temp	193 to 227	°C
Mold Temperature	82.2 to 104	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	30 to 60	rpm

NOTE

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT