

Zenite® ZE55201

Liquid Crystal Polymer
Celanese Corporation

Message:

Zenite® ZE55201 is a 50% mineral/glass fiber reinforced liquid crystal polymer for injection molding. and It is specifically suitable for applications requiring ultra flatness.

General Information			
UL YellowCard	E344082-100831305		
Filler / Reinforcement	Glass \mineral, 50% filler by weight		
Additive	Lubricant		
Features	Lubrication		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.85	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	15800	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	88.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	1.4	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	12500	MPa	ISO 178
Flexural Stress (23°C)	165	MPa	ISO 178
Compressive Stress (1% Strain)	21.3	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.6	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	300	°C	ISO 75-2/B
1.8 MPa, not annealed	290	°C	ISO 75-2/A
Melting Temperature ¹	335	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow	1.5E-5	cm/cm/°C	ISO 11359-2
Lateral	2.7E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Strength	37	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	4.00		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	0.031		IEC 60250

1 MHz	0.031		IEC 60250
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-0		UL 94
1.50 mm	V-0		UL 94
Oxygen Index	41	%	ISO 4589-2
Fill Analysis	Nominal Value	Unit	Test Method
Density of Melt	1.620	g/cm ³	Internal method
Ejection Temperature	270	°C	Internal method
Specific Heat Capacity of Melt	1500	J/kg/°C	Internal method
Thermal Conductivity of Melt	0.40	W/m/K	Internal method
Injection	Nominal Value	Unit	
Drying Temperature	150	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.010	%	
Hopper Temperature	20.0 - 30.0	°C	
Rear Temperature	320 - 330	°C	
Middle Temperature	335 - 345	°C	
Front Temperature	335 - 345	°C	
Nozzle Temperature	335 - 345	°C	
Processing (Melt) Temp	330 - 350	°C	
Mold Temperature	80.0 - 120	°C	
Injection Pressure	50.0 - 150	MPa	
Holding Pressure	50.0 - 150	MPa	
Back Pressure	0.00 - 3.00	MPa	
Injection instructions			
Feed Temperature: 40 to 60°C Zone 4 Temperature: 335 to 345°C			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT