Lifoflex® UV FLAM 60600

Thermoplastic Elastomer

Müller Kunststoffe GmbH

Message:

Lifoflex® UV FLAM 60600 is a Thermoplastic Elastomer (TPE) material. It is available in Europe for extrusion or injection molding. Important attributes of Lifoflex® UV FLAM 60600 are:

Flame Rated

RoHS Compliant

Flame Retardant

Good Adhesion

Good Flexibility

Typical applications include:

Engineering/Industrial Parts

Construction Applications

Electrical/Electronic Applications

Wire & Cable

General Information					
UL YellowCard	E249957-102117137				
Features	Flame Retardant				
	Good Adhesion				
	Good Flexibility				
	Good Processability				
	Halogen Free				
	Low Compression Set				
	Low Smoke Emission				
	Low Toxicity				
Uses	Building Materials				
	Cable Jacketing				
	Electrical Parts				
	Gaskets				
	Grommets				
	Profiles				
Agency Ratings	EU 2003/11/EC				
RoHS Compliance	RoHS Compliant				
Processing Method	Extrusion				
	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	1.03	g/cm³	ISO 1183/A		
Hardness	Nominal Value	Unit	Test Method		
Shore Hardness (Shore A, 3 sec)	60		DIN 53505		

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress - Flow (Yield)	5.50	MPa	DIN 53504
Tensile Elongation - Flow (Break)	840	%	DIN 53504
Compression Set			ISO 815
23°C, 72 hr	21	%	
70°C, 22 hr	49	%	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	V-0		UL 94
	850		

Glow Wire Flammability Index (3.00 mm)

650

°C

IEC 60695-2-12

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

