ALCOM® PBT 700/1 GF30 PTFE15

Polybutylene Terephthalate

ALBIS PLASTIC GmbH

Message:

ALCOM® PBT 700/1 GF30 PTFE15 is a Polybutylene Terephthalate (PBT) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America. Applications of ALCOM® PBT 700/1 GF30 PTFE15 include engineering/industrial parts and automotive.

Characteristics include:

REACH Compliant

RoHS Compliant

High Stiffness

Lubricated

Wear Resistant

| General Information | | | | |
|--|----------------------------------|-------|-------------|--|
| Filler / Reinforcement | Glass Fiber,30% Filler by Weight | | | |
| Additive | PTFE Lubricant (15%) | | | |
| Features | Good Wear Resistance | | | |
| | High Stiffness | | | |
| Uses | Automotive Applications | | | |
| | Bearings | | | |
| | Gears | | | |
| | Machine/Mechanical Parts | | | |
| | Wheels | | | |
| Agency Ratings | EC 1907/2006 (REACH) | | | |
| RoHS Compliance | RoHS Compliant | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Density | 1.65 | g/cm³ | ISO 1183 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Modulus | 10400 | МРа | ISO 527-2 | |
| Tensile Strain (Break) | 2.8 | % | ISO 527-2 | |
| Flexural Modulus | 9300 | MPa | ISO 178 | |
| Flexural Stress | 200 | MPa | ISO 178 | |
| Impact | Nominal Value | Unit | Test Method | |
| Charpy Notched Impact Strength | 9.0 | kJ/m² | ISO 179/1eA | |
| Charpy Unnotched Impact Strength | 50 | kJ/m² | ISO 179/1eU | |
| Thermal | Nominal Value | Unit | Test Method | |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 210 | °C | ISO 75-2/A | |
| Vicat Softening Temperature | 200 | °C | ISO 306/B50 | |
| Injection | Nominal Value | Unit | | |

| Circulation Dryer | 100 to 120 | °C | |
|------------------------|-------------|----|--|
| Desiccant Dryer | 100 to 120 | °C | |
| Drying Time | | | |
| Circulation Dryer | 4.0 to 8.0 | hr | |
| Desiccant Dryer | 2.0 to 4.0 | hr | |
| Processing (Melt) Temp | 250 to 270 | °C | |
| Mold Temperature | 80.0 to 120 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

