

Cevian®-V UG10

Acrylonitrile Butadiene Styrene

PlastxWorld Inc.

Message:

Cevian®-V UG10 is an acrylonitrile butadiene styrene (ABS) product, which contains a 10% glass fiber reinforced material. It can be processed by injection molding and is available in North America. The main characteristics are: flame retardant/rated flame.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.20 - 0.50	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 23°C)	68.6	MPa	ASTM D638
Flexural Modulus (23°C)	3730	MPa	ASTM D790
Flexural Strength (23°C)	98.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	88	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 12.7 mm)	117	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (ALL)	HB		UL 94
Additional Information			
Specific Gravity, ASTM D792, 73°F, 50% RH: 1.11Water Absorption, ASTM D570, 73°F, 24 hr: 0.3 %			
Injection	Nominal Value	Unit	
Drying Temperature	79.4 - 85.0	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	190 - 210	°C	
Middle Temperature	210 - 230	°C	
Front Temperature	230 - 250	°C	
Processing (Melt) Temp	240 - 260	°C	
Mold Temperature	60.0 - 80.0	°C	
Injection Pressure	48.3 - 117	MPa	
Injection Rate	Moderate		
Back Pressure	0.345 - 1.38	MPa	
Screw Speed	40 - 60	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

