

# Daelim Po1y® LD-18A

Low Density Polyethylene

DAELIM INDUSTRIAL CO., LTD.

## Message:

Daelim Po1y®LD-18A is a low density polyethylene product. It is available in the Asia-Pacific region. Daelim Po1y®LD-18A application areas include packaging and food contact applications.

Features include:

Antiblock software

high gloss

General Information			
Additive	High caking resistance		
Features	Highlight		
	High caking resistance		
Uses	Packaging		
Agency Ratings	ASTM D 1248, I, Class A, Cat. 3		
	FDA 21 CFR 177.1520		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.921	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.3	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	30	µm	
Tensile Strength			ASTM D882
MD: Fracture	20.6	MPa	ASTM D882
TD: Fracture	19.6	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	450	%	ASTM D882
TD: Fracture	580	%	ASTM D882
Dart Drop Impact	100	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	10	g	ASTM D1922
TD	7.0	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Haze	6.0	%	ASTM D1003
Additional Information			
Tear Strength, MD, ASTM D-1004: 95kg/cmTear Strength, TD, ASTM D-1004: 90kg/cm			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	160 - 175	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

