

# ESTAPROP KUR 1520 TG05

Polypropylene Copolymer

Cossa Polimeri S.r.l.

Message:

ESTAPROP KUR 1520 TG05 is a Polypropylene Copolymer (PP Copolymer) product filled with 10% mineral. It is available in Europe. Typical application: Automotive.  
Characteristics include:  
Flame Rated  
Impact Resistant

General Information			
Filler / Reinforcement	Mineral,10% Filler by Weight		
Features	High Impact Resistance		
	Low Temperature Impact Resistance		
Uses	Automotive Applications		
	Automotive Bumper		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.2 to 1.5	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1000	MPa	ASTM D638
Tensile Strength (Yield)	15.0	MPa	ASTM D638
Tensile Elongation (Break)	> 200	%	ASTM D638
Flexural Modulus	> 800	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	100	J/m	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	> 50.0	°C	ASTM D1525 <sup>1</sup>
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
NOTE			

1. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

