# Osterlene® LD1019A

## Low Density Polyethylene

### Osterman & Company

#### Message:

Osterlene LD1019 is a series of resins designed for a wide variety of industrial film app lications where high impact strength and excellent drawdown are needed.

LD1019 exhibits good uniformity, ease of processing and good tensile strength.

Osterlene LD1019 meets the requirements of the Food and Drug Administration, 21 CFR Section 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations may apply. Contact your Osterman sales representative for more information.

Specific recommendations can be made only when the end use applications, properties and processing equipment are known. Consult your Osterman sales representative.

General Information					
Additive	Anti-caking agent (4000 ppm)				
Features	Anti-caking property				
	Impact resistance, high				
	Workability, good				
	Good stripping				
Uses	Films				
	Industrial application				
Agency Ratings	FDA 21 CFR 177.1520				
Physical	Nominal Value	Unit	Test Method		
Density	0.919	g/cm³	ASTM D1505		
Melt Mass-Flow Rate (MFR) (190°C/2.					
kg)	1.0	g/10 min	ASTM D1238		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	14.5	MPa	ASTM D638		
Tensile Elongation (Break)	660	%	ASTM D638		
Films	Nominal Value	Unit	Test Method		
secant modulus			ASTM E111		
MD	200	MPa	ASTM E111		
TD	234	MPa	ASTM E111		
Tensile Strength			ASTM D882		
MD: Fracture	24.1	MPa	ASTM D882		
TD: Fracture	16.5	MPa	ASTM D882		
Tensile Elongation			ASTM D882		
MD: Fracture	200	%	ASTM D882		
TD: Fracture	500	%	ASTM D882		
Dart Drop Impact <sup>1</sup>	120	g	ASTM D1709		

Elmendorf Tear Strength	ASTM D1922		
MD	300	g	ASTM D1922
TD	130	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	92.0	°C	ASTM D1525
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

