

Daicel PP PGM7T1

Polypropylene
Daicel Polymer Ltd.

Message:
Daicel PP PGM7T1 is a Polypropylene material filled with 35% glass fiber. It is available in Asia Pacific. Primary attribute of Daicel PP PGM7T1: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	55.0	MPa	ISO 527-2
Flexural Modulus	6000	MPa	ISO 178
Flexural Stress	85.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	160	°C	ISO 75-2/B
Flammability	Nominal Value		Test Method
Flame Rating (NC, BK)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 120	°C	
Drying Time	3.0 to 5.0	hr	
Rear Temperature	140 to 190	°C	
Middle Temperature	160 to 210	°C	
Front Temperature	180 to 230	°C	
Nozzle Temperature	180 to 230	°C	
Mold Temperature	40.0 to 60.0	°C	
Back Pressure	5.00 to 20.0	MPa	
Screw Speed	70 to 90	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

