

Ducaseal Non-Migratory

Flexible Polyvinyl Chloride

Dugdale Plc

Message:

Ducaseal, PVC compounds have been specially developed for ease of processing on co-extrusion and post co-extrusion processes and are suitable for static and dynamic applications. They enable processors to manufacture end products that will adhere to PVC and offer consistently good surface finish - an important characteristic that minimises the ingress of dust and dirt and adds value by increasing product service life. Several tailored grades have been produced, all of which offer attractive cost performance ratios. With a deflection recovery of 25% minimum Ducaseal Static provides a durable seal between PVC profiles and sealed glazing units. Conversely, Ducaseal Dynamic features a deflection recovery of 40% minimum and is designed to offer weatherproof door and window closure seals. For applications involving contact with PC (polycarbonate), such as conservatory roofing seals, Ducaseal Non-Migratory overcomes the problem of stress cracking. Ducaseal Anti-Microbial helps to control bacterial growth in damp and humid conditions, for example in showers and bathrooms. All our compounds are highly specified and meet the performance requirements of BPF 345/2 - PVC-U materials for gaskets and weatherstrips for windows, doors, conservatories and curtain walling. Materials are available in a range of colours alongside black, white or grey - the most popular shades in Europe.

General Information		
Features	Good Adhesion	
	Good Processability	
	Good Surface Finish	
	Good UV Resistance	
	High ESCR (Stress Crack Resist.)	
Uses	Automotive Applications	
	Cable Jacketing	
	Gaskets	
	Hose	
	Sealing Devices	
Appearance	Black	
	Colors Available	
	White	
Forms	Pellets	
Processing Method	Coextrusion	
	Extrusion	
Physical	Nominal Value	Unit
Specific Gravity	1.20 to 1.40	g/cm ³
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	65 to 90	
Mechanical	Nominal Value	Unit
Tensile Strength	> 10.0	MPa

Tensile Elongation (Break)	250 to 450	%
Thermal	Nominal Value	Unit
Service Temperature	-10 to 80	°C
Deflection Recovery - 14 days (55°C)	> 25.0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

