

Luran® SAN 51

Styrene Acrylonitrile

Styrolution

Message:

Luran SAN 51 is an injection molding grade of SAN with excellent chemical resistance and toughness.

General Information			
UL YellowCard	E256400-520825		
Features	Good Chemical Resistance Good Toughness		
Uses	Appliances Electrical/Electronic Applications		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	15.0	cm ³ /10min	ISO 1133
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	106	°C	ASTM D1525 ¹
NOTE			
1.	Rate B (120°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

