

Manner Flexible PVC C8070

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

Message:

80°C Clear General Purpose for Injection Molding compound for appliance harness compounds or Profile Extrusion Compound. Meets aging of 168 Hours at 113°C.

General Information			
Features	General Purpose		
Uses	Appliance Components Profiles		
Appearance	Clear/Transparent		
Processing Method	Injection Molding Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17 to 1.21	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	17.9	MPa	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Injection	Nominal Value	Unit	
Processing (Melt) Temp	171 to 182	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

