

LEXAN™ 923X resin

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

LEXAN923x is a UV stabilized high flow impact modified injection molding (IM) grade. This resin offers UL94 V0 @ 1.5mm flame retardancy based on non-bromine, non-chlorine FR systems, low temperature ductility characteristics and excellent processability with opportunities for shorter IM cycle times compared to standard PC. LEXAN 923x resin is a product available in a wide range of opaque colors and may be an excellent candidate for a wide range of applications.

General Information			
Additive	Impact modifier		
	UV stabilizer		
Features	Chlorine Free		
	Impact modification		
	Good UV resistance		
	Workability, good		
	High liquidity		
	Bromine-free		
	ductility		
Appearance	Flame retardancy		
	Opacity		
Processing Method	Available colors		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	16	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.80	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2100	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	58.0	MPa	ASTM D638
Fracture	60.0	MPa	ASTM D638
Tensile Elongation ³			ASTM D638
Yield	6.0	%	ASTM D638
Fracture	110	%	ASTM D638
Flexural Modulus ⁴ (50.0 mm Span)	2400	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 50.0 mm Span)	90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			ASTM D256
-30°C	650	J/m	ASTM D256
23°C	780	J/m	ASTM D256
Instrumented Dart Impact (23°C, Total Energy)			ASTM D3763
	65.0	J	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	123	°C	ASTM D648
Vicat Softening Temperature	140	°C	ASTM D1525 ⁶
Linear thermal expansion coefficient			ASTM E831
Flow: -40 to 40°C	6.1E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	6.2E-5	cm/cm/°C	ASTM E831
RTI Elec	125	°C	UL 746
RTI Imp	115	°C	UL 746
RTI	120	°C	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		UL 94
3.00 mm	5VA		UL 94
Glow Wire Flammability Index (1.50 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
1.50 mm	825	°C	IEC 60695-2-13
3.00 mm	825	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	270 - 295	°C	
Middle Temperature	280 - 305	°C	
Front Temperature	295 - 315	°C	
Nozzle Temperature	290 - 310	°C	
Processing (Melt) Temp	295 - 315	°C	
Mold Temperature	70.0 - 95.0	°C	
Back Pressure	0.300 - 0.700	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.025 - 0.076	mm	
NOTE			
1.	5.0 mm/min		
2.	Type 1, 50mm/min		
3.	Type 1, 50mm/min		
4.	1.3 mm/min		

5.	1.3 mm/min
6.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

