

# RTP 2287

Polyetheretherketone

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'  
The data for this material has not been recently verified.  
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Carbon Fiber,40% Filler by Weight		
Features	Electrically Conductive		
	Good Thermal Stability		
RoHS Compliance	Contact Manufacturer		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.050 to 0.10	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.12	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	37200	MPa	ASTM D638
Tensile Strength (Yield)	269	MPa	ASTM D638
Tensile Elongation (Break)	1.1	%	ASTM D638
Flexural Modulus	22100	MPa	ASTM D790
Flexural Strength (Yield)	379	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	85	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	750	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	288	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	30	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.10	%	

Suggested Max Regrind	20	%
Rear Temperature	357 to 399	°C
Middle Temperature	366 to 418	°C
Front Temperature	385 to 427	°C
Mold Temperature	121 to 204	°C
Injection Pressure	68.9 to 124	MPa
Back Pressure	0.345 to 0.689	MPa
Screw Speed	60 to 90	rpm
Clamp Tonnage	6.9 to 11	kN/cm <sup>2</sup>

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

