

EnDura® V91J

Fluoroelastomer

Precision Polymer Engineering Ltd.

Message:

Recognising the demanding challenges in the oil and gas exploration and extraction industry, PPE has developed the most technically advanced range of elastomer materials to meet the needs of sealing applications operating in the most severe conditions.

The EnDura® range of elite materials has been specifically formulated for Explosive Decompression (ED) resistance in downhole, surface and subsea oilfield equipment.

EnDura® V91J provides outstanding mechanical strength and high pressure performance.

Key Attributes

Excellent Explosive Decompression resistance

Tested to Norsok M-710 standard

Tested to Total specification GS PVV 142 03/01

Tested to NACE standards: TM0297 (ED) & TM0187 (Sour Gas)

Wide resistance to oilfield chemicals

Versatile material with good compression set characteristics providing excellent sealing properties

Typical Applications

Low temperature and high pressure environments

Exploration and drilling equipment

Completion equipment

Subsea valves and pumps

Compressors

Blow-out preventors (BOPs)

Feed throughs

O-rings, T-section seals, special profiles and custom-made seals

General Information			
Features	High strength		
	Good chemical resistance		
	Oil resistance		
Uses	Pump parts		
	Low temperature application		
	Valve/valve components		
	Seals		
	Oil/Gas Supplies		
Appearance	Black		
Hardness	Nominal Value	Test Method	
IRHD Hardness	90	ASTM D1415, ISO 48	
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	24.0	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	210	%	ASTM D412, ISO 37
Compression Set (200°C, 24 hr)	24	%	ASTM D395, ISO 815
Thermal	Nominal Value	Unit	ASTM D1329
Maximum Operating Temperature	225	°C	
Low Temperature Resistance - TR10	-12	°C	

Additional Information	Nominal Value	Unit	Test Method
------------------------	---------------	------	-------------

Minimum Operating Temperature: -18°C (-1°F)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

