

Trilliant™ HC HC6620-0033 RS Natural

Polyamide 66
PolyOne Corporation

Message:

The Trilliant® specialty compounds offer a complete system of specialty engineered materials, certified processes, services and technical support that enable healthcare OEM's to get to market ahead of the competition. When specified, Trilliant® compounds may incorporate agency rated materials that meet USP Class VI, FDA or ISO 10993 testing requirements.

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Features	Biocompatible		
	Good Chemical Resistance		
	Good Colorability		
	Medium Impact Resistance		
	Specialty Grade		
Uses	Hospital Goods		
	Housings		
	Medical Devices		
	Medical/Healthcare Applications		
Agency Ratings	USP Class VI		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.30	%	
Across Flow	1.7	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	190	MPa	ASTM D638
Tensile Elongation ² (Break)	12	%	ASTM D638
Flexural Modulus	8960	MPa	ASTM D790
Flexural Strength	276	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	110	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Annealed, 3.18 mm)	> 245	°C	ASTM D648

Melting Temperature	282 to 293	°C
Injection	Nominal Value	Unit
Drying Temperature	82.2	°C
Drying Time	3.0	hr
Mold Temperature	60.0 to 71.1	°C
NOTE		
1.	Type I, 51 mm/min	
2.	Type I, 51 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

