Moplen HP516J

Polypropylene Homopolymer LyondellBasell Industries

Message:

lyondellBasell Australia's Polypropylene grade HP516J is a medium flow homopolymer with a conventional molecular weight distribution and is specially designed for metallised film applications HP516J is designed for the production of biaxially oriented metallised films (BOPP) for high quality packaging and laminates. HP516J gives reliable and consistent processing on BOPP tenter lines, providing films with a good balance of properties.

General Information			
Features	Food Contact Acceptable		
	Homopolymer		
	Medium Flow		
Uses	Bi-axially Oriented Film		
	Film		
Agency Ratings	FDA 21 CFR 177.1520(a) 1		
	FDA 21 CFR 177.1520(c) 1.1		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm³	ISO 1183/D
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	3.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	77		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	33.0	MPa	ISO 527-2
Flexural Modulus	1500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	4.5	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa,			
Unannealed)	84.0	°C	ISO 75-2/B
Vicat Softening Temperature	155	°C	ISO 306/A50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

