

RAMOFIN PPC370B73

Polypropylene Copolymer
Polyram Ram-On Industries

Message:
73% MINERAL FILLED POLYPROPYLENE FOR HEAVY DENSITY INJECTION MOULDING APPLICATIONS.

General Information			
Filler / Reinforcement	Mineral,73% Filler by Weight		
Features	High Density		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.10	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow	0.80 to 1.2	%	ISO 2577
--	0.80 to 1.2	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1700	MPa	ASTM D638, ISO 527-2
Tensile Strength (Yield)	10.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	> 10	%	ASTM D638, ISO 527-2
Flexural Modulus	2220	MPa	ASTM D790, ISO 178
Flexural Strength	20.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	100	J/m	ASTM D256
23°C	10	kJ/m ²	ISO 180
Injection	Nominal Value	Unit	
Rear Temperature	190 to 220	°C	
Middle Temperature	200 to 225	°C	
Front Temperature	205 to 230	°C	
Mold Temperature	30.0 to 65.0	°C	
Injection Pressure	70.0 to 105	MPa	
Holding Pressure	35.0 to 70.0	MPa	
Back Pressure	0.350 to 0.700	MPa	
Screw Speed	60 to 90	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

