

Jam PE 15YF6

Linear Low Density Polyethylene
Jam Petrochemical Company

Message:

Jam PE 15YF6 is a Linear Low Density Polyethylene product. It is available in Africa & Middle East. Typical application: Film.

General Information			
Uses	Film		
Physical	Nominal Value	Unit	Test Method
Density	0.915 to 0.917	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.60	g/10 min	ASTM D1238
Flow Rate Ratio	32.0		ASTM D1238
Fish Eye	100	No./m ²	
Titanium	3	ppm	
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	
Tensile Strength			ASTM D882
MD : Yield,25 µm, Blown Film	12.5	MPa	
TD : Yield,25 µm, Blown Film	13.4	MPa	
MD : Break, 25 µm,Blown Film	33.0	MPa	
TD : Break, 25 µm,Blown Film	35.0	MPa	
Tensile Elongation			ASTM D882
MD : Break, 25 µm,Blown Film	860	%	
TD : Break, 25 µm,Blown Film	700	%	
Dart Drop Impact (25 µm, Blown Film)	150	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm, Blown Film	510	g	
TD : 25 µm, Blown Film	170	g	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.0 µm, Blown Film)	45		ASTM D1790
Haze (25.0 µm, Blown Film)	18	%	ASTM D1003
Yellowness Index (0.0250 mm)	0.0	YI	ASTM D1925

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

