

EcoVid 30GBTFH

Polylactic Acid

Greener Polymers Inc.

Message:

EcoVid-30GBTFH is a General Purpose Ingeo PLA and bio-composite material blend suitable for Thermoforming processes with a High Heat resistance index. The material, rated for 178F/80°C and could be frozen to -32°C. Mould crystallization will increase the heat deflection from 80°C to 110°C+ depending on the application.

Composition: Ingeo PLA content with bio-degradable and HDT additives.

Applications: EcoVid-30GBTFH is a heat resistant blend for single use thermoformed disposable food trays, packaging inserts, clamshells, platters, etc.

General Information			
Additive	Unspecified additive		
Features	Updatable resources		
	Heat resistance, high		
	Biodegradable		
Uses	Single-Use Applications		
	Thermoforming Applications		
	Non-specific food applications		
	Food service sector		
	General		
Processing Method	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	6.0	g/10 min	ASTM D1238
210°C/2.16 kg	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 - 0.50	%	
Relative Viscosity	2.5		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	62.1	MPa	ASTM D638
Tensile Elongation (Break)	3.5	%	ASTM D638
Flexural Strength	108	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	16	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	55.0 - 60.0	°C	ASTM D3418
Vicat Softening Temperature	130	°C	ASTM D1525
Melting Temperature	130 - 180	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	155 - 170	°C	ASTM D3418

Heat Distortion	80 - 110	°C	ASTM E2092
Clarity	NIL		
Additional Information			
Vapour Barrier Transmission Rate (ASTM E380): 20.1636 (sd +/- 0.3537)Oxygen Permeability (ASTM E380): 53.481 (sd +/- 0.249)			
Injection	Nominal Value	Unit	
Hopper Temperature	145 - 155	°C	
Rear Temperature	145 - 165	°C	
Middle Temperature	165 - 195	°C	
Front Temperature	165 - 195	°C	
Nozzle Temperature	165 - 180	°C	
Back Pressure	1.03 - 2.76	MPa	
Screw Speed	35 - 65	rpm	
Injection instructions			
Mould Cycle Time: 19-35 secs			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

