

Toughblend® PP-1302

Polypropylene

Colour Image Plastic Compound Sdn. Bhd. (CIPC)

Message:

Toughblend® PP-1302 is a glass fiber reinforced coupled polypropylene compound. It's offering high stiffness and dimensional stability properties.

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
	Mineral,15% Filler by Weight		
Features	Chemically Coupled		
	Good Dimensional Stability		
	High Stiffness		
Uses	Automotive Applications		
	Industrial Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.20 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	45.0	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	5000	MPa	ASTM D790
Flexural Strength	58.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	60	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 4.00 mm	135	°C	
1.8 MPa, Unannealed, 4.00 mm	120	°C	
Flammability	Nominal Value	Test Method	
Flame Rating (1.60 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	190 to 200	°C	
Middle Temperature	200 to 210	°C	

Front Temperature	210 to 220	°C
Nozzle Temperature	220 to 230	°C
Processing (Melt) Temp	190 to 230	°C
Mold Temperature	60.0 to 70.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

