

DuPure® SU 76 A

Polypropylene Impact Copolymer

Ducor Petrochemicals BV

Message:

Description

DuPure SU 76 A is a heterophasic copolymer, suitable for injection moulding applications. The product is nucleated and contains anti-electrostatic properties, very good flowability and a good balance of stiffness and impact strength.

Applications

DuPure SU 76 A is suitable for: general injection moulding, packaging.

General Information			
Additive	Antistatic		
	Nucleating Agent		
Features	Antistatic		
	Food Contact Acceptable		
	General Purpose		
	Good Flow		
	Impact Copolymer		
	Nucleated		
Uses	General Purpose		
	Packaging		
Agency Ratings	EC 1907/2006 (REACH)		
	EC 1935/2004		
	EN 71-3		
	EU 10/2011		
	EU 2000/53/EC		
	EU 2002/96/EC (WEEE)		
	EU 2005/84/EC		
	EU 94/62/EC		
	FDA 21 CFR 177.1520(a) 3 (i)		
	FDA 21 CFR 177.1520(c) 3.1a		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	48	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method

Ball Indentation Hardness (H 358/30)	62.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1400	MPa	ISO 527-2/1
Tensile Stress (Yield)	27.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	5.0	%	
Break	40	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	3.0	kJ/m ²	
-20°C	3.2	kJ/m ²	
0°C	4.0	kJ/m ²	
23°C	6.5	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	65	kJ/m ²	
-20°C	75	kJ/m ²	
0°C	100	kJ/m ²	
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A
-30°C	3.0	kJ/m ²	
23°C	5.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	90.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	53.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	151	°C	ISO 306/A
--	70.0	°C	ISO 306/B
Melting Temperature (DSC)	163	°C	ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT