

OXPEKK® MG100

Polyetherketoneketone

Oxford Performance Materials, Inc.

Message:

OXPEKK® MG100 is a Polyetherketoneketone (PEKK) material. It is available in Europe or North America.
Typical application of OXPEKK® MG100: Medical/Healthcare

General Information			
Features	Amorphous		
Uses	Medical/Healthcare Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (380°C/8.4 kg)	35 to 40	g/10 min	ASTM D1238
Molding Shrinkage - Flow	< 0.50	%	ASTM D955
Water Absorption (24 hr)	< 0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	86		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3450	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	103	MPa	
Break	89.6	MPa	
Tensile Elongation			ASTM D638
Yield	6.0	%	
Break	80	%	
Flexural Modulus	3380	MPa	ASTM D790
Flexural Strength (5.0% Strain)	138	MPa	ASTM D790
Compressive Strength	103	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	141	°C	ASTM D648
Glass Transition Temperature	155	°C	DSC
Melting Temperature	307	°C	DSC
CLTE - Flow	7.7E-5	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

