

Maxxam™ PPH-30T Nat

Polypropylene Homopolymer

PolyOne Corporation

Message:

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

General Information			
UL YellowCard	E76261-101413514		
Filler / Reinforcement	Filler,30% Filler by Weight Talc		
Features	General Purpose Homopolymer		
Uses	Automotive Applications Construction Applications Consumer Applications General Purpose Industrial Applications		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Specific Volume	0.871	cm ³ /g	ASTM D792
Molding Shrinkage - Flow	0.60 to 1.2	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	31.7	MPa	ASTM D638
Tensile Elongation ² (Break)	25	%	ASTM D638
Flexural Modulus	3720	MPa	ASTM D790
Flexural Strength	53.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	32	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Annealed, 3.18 mm)	127	°C	ASTM D648
Flammability	Nominal Value		Test Method

Flame Rating (1.50 mm, ALL)	HB	UL 94
NOTE		
1.	Type I, 51 mm/min	
2.	Type I, 51 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

