

Ducor® 2340 P

Polypropylene Impact Copolymer

Ducor Petrochemicals BV

Message:

Ducor 2340 P is a nucleated heterophasic propylene copolymer. Ducor 2340 P combines a good stiffness with good impact strength. Typical applications are housewares, cylindrical containers and crates, furniture.
Food Contact Applications: This grade is in compliance with most regulations regarding food contact applications (EU, FDA). Specific information is available upon request.

General Information			
Additive	Nucleating Agent		
Features	Food Contact Acceptable		
	Good Impact Resistance		
	Good Stiffness		
	Impact Copolymer		
	Nucleated		
Uses	Containers		
	Crates		
	Furniture		
	Household Goods		
Agency Ratings	EC 1907/2006 (REACH)		
	EC 1935/2004		
	EN 71-3		
	EU 10/2011		
	EU 2000/53/EC		
	EU 2002/96/EC (WEEE)		
	EU 2005/84/EC		
	EU 94/62/EC		
	FDA 21 CFR 177.1520(a) 3 (i)		
	FDA 21 CFR 177.1520(c) 3.1a		
	FDA 21 CFR 177.1520(c) 3.2a		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	63.0	MPa	ISO 2039-1

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1400	MPa	ISO 527-2/1
Tensile Stress (Yield)	28.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	6.0	%	
Break	> 50	%	
Shear Modulus	730	MPa	ISO 6721-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	2.0	kJ/m ²	
-20°C	2.5	kJ/m ²	
0°C	3.0	kJ/m ²	
23°C	6.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	45	kJ/m ²	
-20°C	50	kJ/m ²	
0°C	100	kJ/m ²	
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A
-30°C	2.0	kJ/m ²	
-20°C	2.5	kJ/m ²	
0°C	3.0	kJ/m ²	
23°C	5.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	90.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	53.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	151	°C	ISO 306/A
--	68.0	°C	ISO 306/B
Melting Temperature (DSC)	163	°C	ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT