

Luxus PP 16192

Polypropylene

Luxus Limited

Message:

Suitable for general injection mouldings requiring heat resistance, stiffness and high melt flow. Suitable for applications requiring food approval.

General Information			
Filler / Reinforcement	Talc,30% Filler by Weight		
Recycled Content	Yes		
Features	Food Contact Acceptable		
	Good Stiffness		
	High Flow		
	High Heat Resistance		
Uses	Non-specific Food Applications		
Appearance	White		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	21	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	25.0	MPa	ISO 527-2
Tensile Strain (Break)	5.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	2.0	kJ/m ²	ISO 180
Multi-Axial Instrumented Impact Peak Force	1050	N	ISO 527

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT