NuSil MED-4565

Rubber

NuSil Technology

Message:

NuSil Technology's unrestricted materials may be considered for long-term implant applications (greater than 29 days).

HCRs can be used for extrusion of tubing and profiles (rod or ribbon), in calendared sheeting for die-cutting, or in compression or transfer molded parts such as balloons, gaskets or o-rings. HCRs are clay-like in the uncured state and when cured generally exhibit very high mechanical properties and low modulus.

HCRs with a peroxide cure system have a long history in implant applications. The cure mechanism can be vinyl specific or non vinyl specific. Non vinyl specific peroxide catalysts are more commonly used with HCRs than vinyl specific peroxide catalysts. Comments: UNCATALYZED

| General Information | | |
|--------------------------------|---------------------------|-------|
| Uses | Washer | |
| | Pipe fittings | |
| | Balloon application | |
| | Profile | |
| | Medical/nursing supplies | |
| | | |
| Agency Ratings | USP Class VI | |
| Processing Method | Extrusion | |
| | Resin transfer molding | |
| | Profile extrusion molding | |
| | Compression molding | |
| | Calendering | |
| | | |
| Mechanical | Nominal Value | Unit |
| Tensile Strength (200% Strain) | 3.10 | MPa |
| Thermoset | Nominal Value | Unit |
| Post Cure Time (177°C) | 2.0 | hr |
| Additional Information | Nominal Value | Unit |
| Cure System | Peroxide | |
| Plasticity: 115 mils | | |
| Uncured Properties | Nominal Value | Unit |
| Density | 1.21 | g/cm³ |
| Curing Time (116°C) | 0.083 | hr |
| Cured Properties | Nominal Value | Unit |
| Shore Hardness (Shore A) | 65 | |
| Tensile Strength | 8.27 | MPa |
| Tensile Elongation at Break | 500 | % |
| Tear Strength | 35.0 | kN/m |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

