Globalene® SI4351

Polypropylene Alloy

Lee Chang Yung Chemical Industry Corp.

Message:

Globalene® Sl4351 is a Polypropylene Alloy (PP Alloy) material. It is available in Asia Pacific or North America for injection molding. Important attributes of Globalene® Sl4351 are: RoHS Compliant Good Processability High Stiffness Low Shrinkage Typical applications include: Appliances Household Applications Housings

General Information			
Features	Good Moldability		
	High Stiffness		
	Low Shrinkage		
Uses	Appliances		
	Household Goods		
	Housings		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	14	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	88		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	25.9	MPa	ASTM D638
Tensile Elongation (Yield)	2.7	%	ASTM D638
Flexural Modulus	2400	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	26	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	139	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

