

ICORENE® 3935

Polyethylene Copolymer

ICO Polymers SA, A Division of A. Schulman

Message:

ICORENE® 3935 is a Polyethylene Copolymer (PE Copolymer) product. It can be processed by rotational molding and is available in Latin America.

Applications of ICORENE® 3935 include food contact applications and tanks.

Characteristics include:

Butene Comonomer

Copolymer

Food Contact Acceptable

Good Processability

Impact Resistant

General Information			
Features	Butene Comonomer Copolymer Food Contact Acceptable Good Impact Resistance Good Processability		
Uses	Tanks		
Agency Ratings	FDA 21 CFR 177.1520		
Appearance	Natural Color		
Forms	Powder		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.939	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (F50)	300	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	19.0	MPa	ASTM D638
Tensile Elongation ² (Break)	> 1000	%	ASTM D638
Flexural Modulus ³	740	MPa	ASTM D790
Aging	Nominal Value	Unit	Test Method
Accelerated Aging	5.5	month	ASTM G26
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	115	°C	ASTM D1525
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

