

TROSIFOL® BG R15

Polyvinyl Butyral
Kuraray Co., Ltd.

Message:

TROSIFOL® BG R15 is a Polyvinyl Butyral (PVB) material. It is available in Asia Pacific, Europe, or North America.

General Information			
Appearance	Blue		
	Blue-Green		
	Brown		
	Clear/Transparent		
	Grey		
	Light Brown		
	Translucent		
	White		
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm³	DIN 53479
Films	Nominal Value	Unit	Test Method
Tensile Strength	> 23.0	MPa	ISO 527-3
Tensile Elongation (Break)	> 280	%	ISO 527-3
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	2.2E-4	cm/cm/°C	
Specific Heat	1850	J/kg/°C	DIN 52616
Thermal Conductivity	0.20	W/m/K	DIN EN 12939
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+11	ohms	DIN 53482
Optical	Nominal Value		Test Method
Refractive Index	1.482		DIN 53491

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT