

Nylene® 9110 G33

Polyamide 610

Custom Resins Group

Message:

33% glass fiber reinforced nylon 6/10 injection molding grade.

Has the high strength and stiffness of reinforced nylon, while also having the reduced moisture pick-up associated with nylon 6/10

Suitable for pump housings, inlet housings, fittings, and other uses where moisture pickup may be a concern

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Features	High Stiffness		
	High Strength		
	Low Moisture Absorption		
Uses	Fittings		
	Housings		
	Pump Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	145	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	25	%	ASTM D638
Flexural Modulus (23°C)	7580	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	196	°C	ASTM D648
Peak Melting Temperature	214	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

