New-prene™ 8265N

Polypropylene + EPDM Rubber

Total Polymer Vision (Suzhou) Co., LTD

Message:

A natural color flame retardant EPDM/PP thermoplastic vulcanizate. This material combines good physical properties and chemical resistance for use in wire and cable applications. This product contains non-ether brominated compounds. It is RoHS compliant. It is polyolefin based and completely recyclable.

| General Information | | | |
|--|---------------------------|---------|-------------|
| Features | Brominated | | |
| | Flame Retardant | | |
| | Good Chemical Resistance | | |
| | Recyclable Material | | |
| | | | |
| Uses | Wire & Cable Applications | | |
| RoHS Compliance | RoHS Compliant | | |
| Appearance | Natural Color | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| Hardness | Nominal Value | | Test Method |
| Durometer Hardness (Shore A) | 65 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 4.50 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 480 | % | ASTM D412 |
| Aging | Nominal Value | Unit | Test Method |
| Change in Tensile Strength in Air (135°C, 168 hr) | 1.9 | % | ASTM D573 |
| Change in Ultimate Elongation in Air (135°C, 168 hr) | -17 | % | ASTM D573 |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity ¹ | 4.0E+14 | ohms·cm | IEC 60093 |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating | V-0 | | UL 94 |
| Extrusion | Nominal Value | Unit | |
| Drying Temperature | 80.0 | °C | |
| Drying Time | 3.0 | hr | |
| Cylinder Zone 1 Temp. | 165 | °C | |
| Cylinder Zone 2 Temp. | 175 to 190 | °C | |
| Cylinder Zone 3 Temp. | 180 to 200 | °C | |
| Melt Temperature | 170 to 210 | °C | |
| Die Temperature | 180 to 200 | °C | |
| | | | |

NOTE

1. 20°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

