

NILAMID® A3 MGF2010

Polyamide 66

Nilit Plastics

Message:

NILAMID® A3 MGF2010 is a Polyamide 66 (Nylon 66) compound, 10% glass fiber reinforced, 20% mineral filled, high heat stabilized.

This compound is intended for injection molding.

NILAMID® A3 MGF2010 is primarily designed for the Automotive industry. It is also suitable for Electrical and Electronic or Industrial & Consumer applications.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight Mineral,20% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Uses	Automotive Applications Consumer Applications Electrical/Electronic Applications Industrial Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.39	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 23°C	1.4	%	
Flow : 23°C	0.90	%	
Water Absorption			ISO 62
23°C, 24 hr	2.0	%	
Saturation, 23°C	7.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	5800	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	110	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	35	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	250	°C	ISO 75-2/B
1.8 MPa, Unannealed	250	°C	ISO 75-2/A
Continuous Use Temperature ¹	120	°C	IEC 60216

Ball Pressure Test			IEC 60695-10-2
125°C	Pass		
165°C	Pass		
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	1.0E+15	ohms·cm	IEC 60093
Comparative Tracking Index (3.20 mm, Solution A)	550	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
3.20 mm	HB		
NOTE			
1.	20000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

