

# Lucent PA G66-33

Polyamide 66  
Lucent Polymers, Inc.

Message:  
33% Glass Fiber Reinforced, Nylon 66  
Colors Available  
Add "H" for Heat Stabilized  
Add "HU" for Weatherable  
Typical Properties, Dry as Molded

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Appearance	Colors Available		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	138	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength	221	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	243	°C	ASTM D648
Peak Melting Temperature	250 to 265	°C	ASTM D789

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT