

TOTAL Polyethylene LDPE 1200 MN 18 C

Low Density Polyethylene
TOTAL Refining & Chemicals

Message:

LDPE 1200 MN 18 C is a low density polyethylene made by high pressure autoclave process.
Application examples: flexible moulding, handles, closures, household items, toys, various containers (basins, buckets ...) and master-batches.

General Information			
Uses	Handle		
	Composite		
	Household goods		
	Masterbatch		
	Container		
	Shell		
	Toys		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Particle		
Processing Method	Injection molding		
Multi-Point Data	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density			
--	0.918	g/cm ³	ISO 1183
--	918	kg/m ³	ISO 1183 ¹
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	22	g/10 min	ISO 1133
Melt volume-flow rate (190°C/2.16 kg)	26.0	cm ³ /10min	ISO 1133 ²
Molding Shrinkage	2.0 - 4.0	%	Internal method
Water Absorption (Saturation)	0.010	%	ISO 62 ³
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	51		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
--	160	MPa	ISO 527-2
--	170	MPa	ISO 527-2 ⁴
Tensile Stress			
Yield	8.00	MPa	ISO 527-2
Fracture	8.00	MPa	ISO 527-2
Tensile Strain			
Yield	15	%	ISO 527-2 ⁵
Fracture	250	%	ISO 527-2

Tensile Elongation at Break	> 50	%	ISO 527-2 ⁶
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	85.0	°C	ISO 306
50°C/h, B (50N)	88.0	°C	ISO 306 ⁷
Melting Temperature (DSC)			
--	106	°C	ISO 3146
-- ⁸	107	°C	ISO 11357-3 ⁹
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093 ¹⁰
Volume Resistivity	> 1.0E+13	ohms·m	IEC 60093 ¹¹
Relative Permittivity (100 Hz)	2.00		IEC 60250 ¹²
Dissipation Factor			IEC 60250 ¹³
100 Hz	2.0E-4		IEC 60250
1 MHz	2.0E-4		IEC 60250
Comparative Tracking Index	600		IEC 60112 ¹⁴
Flammability	Nominal Value	Unit	Test Method
Burning Behav. at 1.6mm nom. thickn. (1.60 mm)	HB		ISO 1210 ¹⁵
Oxygen Index	18	%	ISO 4589-2 ¹⁶
Additional Information			
The value listed as Melting Temperature, ISO 3146, was tested in accordance with ISO 11357.			
Injection	Nominal Value	Unit	
Mold Temperature	30.0 - 40.0	°C	
Injection instructions			
Advised Temperature Profile: 160 to 240°C Hold Pressure: 20 to 50% of injection pressure			
NOTE			
1.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		
2.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		
3.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		
4.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		
5.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		
6.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		
7.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		
8.	10 °C/min		
9.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		

10.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
11.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
12.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
13.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
14.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
15.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
16.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

