

Andur 74-AGP

Polyurethane (Polyether, TDI)
Anderson Development Company

Message:

Andur 74-AGP is a Polyurethane (Polyether, TDI) (PUR-Ether/TDI) product. It is available in North America. Typical application: Automotive.

General Information			
Features	Low Hysteresis		
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Apparent Density	1.02	g/cm ³	ASTM D1895
Molding Shrinkage - Flow	1.2	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	73		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	29.0	MPa	ASTM D638
Tensile Elongation (Yield)	700	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	2.59	MPa	
300% Strain	4.14	MPa	
Compression Set	35	%	ASTM D395
Thermoset	Nominal Value	Unit	Test Method
Pot Life (70°C)	20 to 30	min	
Thermoset Mix Viscosity (70°C)	10200	cP	ASTM D2393

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT