

Boda BDF-KK2601

Fluoroelastomer

Chenguang Fluoro & Silicone Elastomers Co., Ltd.

Message:

Material Type: Brown fluoroelastomer compound, hardness Shore A 55-65.
Based on bisphenol curable copolymers.
Features: Excellent rheology, excellent mold release and good compression set.
Process Methods: Suitable for compression, transfer, injection and extrusion molding processes.
Applications: O-rings, gaskets and other parts.
Lab Testing Curing Condition:
Press Curing: 10min@170°C.
Oven: (8+16)hrs@230°C

General Information	
Features	Good Mold Release
	Low Compression Set
Uses	Gaskets
Appearance	Brown
Processing Method	Compression Molding
	Extrusion
	Injection Molding
	Resin Transfer Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.92	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	60		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	11.2	MPa	ASTM D412
Tensile Elongation (Break)	250	%	ASTM D412
Compression Set ¹ (200°C, 70 hr)	17	%	ASTM D395
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (250°C, 70 hr)	-4.0	%	ASTM D573
Change in Ultimate Elongation in Air (250°C, 70 hr)	-10	%	ASTM D573
Change in Durometer Hardness in Air (250°C, 70 hr)	1.0		ASTM D573
Change in Tensile Strength (23°C, 70 hr, in Reference Fuel C)	-10	%	ASTM D471
Change in Ultimate Elongation (23°C, 70 hr, in Reference Fuel C)	-11	%	ASTM D471

Change in Durometer Hardness (23°C, 70 hr, in Reference Fuel C)	-3.0		ASTM D471
Change in Volume (23°C, 70 hr, in Reference Fuel C)	3.0	%	ASTM D471
NOTE			
1.	6 mm Buttons		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT