

AKROLOY® PA GF 50 black (2706)

Polyamide 66 + PA 6I/6T

AKRO-PLASTIC GmbH

Message:

AKROLOY® PA GF 50 black (2706) is a 50% glass fibre reinforced polyamide-blend with very high stiffness and strength, even in conditioned state. Applications are components with high dimensional stability, independent from moisture content. AKROLOY PA GF 50 black is an alternative for aluminium- and zinc diecast alloys.

General Information				
Filler / Reinforcement		Glass Fiber,50% Filler by Weight		
Features		Good Dimensional Stability		
		High Stiffness		
		High Strength		
Uses		Metal Replacement		
Appearance		Black		
Resin ID (ISO 1043)		PA66 + PA6I/6T GF50		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.59	--	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	9.00	--	cm ³ /10min	ISO 1133
Spiral Flow	54.0	--	cm	Internal Method
Molding Shrinkage				ISO 294-4
Across Flow	0.50	--	%	
Flow	< 0.30	--	%	
Water Absorption (Saturation, 23°C)	3.5 to 4.0	--	%	ISO 62
Humidity Absorption - 62% RH (70°C)	1.1	--	%	ISO 1110
Temperature Index				IEC 216
50% Loss of Tensile Strength, 20000 hr	110 to 130	--	°C	
50% Loss of Tensile Strength, 5000 hr	140 to 150	--	°C	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 961/30)	290	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	17500	16500	MPa	ISO 527-2/1
Tensile Stress (Break)	250	220	MPa	ISO 527-2/5
Tensile Strain (Break)	3.0	3.0	%	ISO 527-2/5
Flexural Modulus ¹	16400	--	MPa	ISO 178
Flexural Stress ²	380	--	MPa	ISO 178

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	15	--	kJ/m ²	
23°C	17	17	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	95	--	kJ/m ²	
23°C	110	100	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	245	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	225	--	°C	ISO 75-2/A
Vicat Softening Temperature	242	--	°C	ISO 306/B50
Melting Temperature ³	255	--	°C	DIN EN 11357-1
CLTE				ISO 11359-2
Flow : 23 to 80°C	1.5E-5	--	cm/cm/°C	
Transverse : 23 to 80°C	6.5E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.5E+17	--	ohms	IEC 60093
Volume Resistivity	9.1E+13	--	ohms·cm	IEC 60093
Relative Permittivity (1 MHz)	4.42	--		IEC 60250
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate ⁴ (1.00 mm)	< 100	--	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB	--		UL 94
Glow Wire Flammability Index (1.60 mm)	700	--	°C	IEC 60695-2-12
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			
3.	10 K/min, DSC			
4.	>1 mm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

