

# ELASTOSIL® RT 713

Silicone

Wacker Chemie AG

## Message:

Silicone Rubber, RTV-2

Bonding & Sealing, Adhesives and Sealants

Bonding & Sealing, Renewable Energies

Elect. Control Devices/Protect Sensors, Electronics

Elect. Control Devices/Protect Sensors, Automotive & Transportation

Electronic Control Devices, Electrical Industry

Electronic Control Devices, Automotive & Transportation

Electronic Control Devices, Electronics

General Information			
Uses	Adhesives		
	Bonding		
	Sealants		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Grey		
Density			
--	0.750	g/cm <sup>3</sup>	ISO 2781
--	0.750	g/cm <sup>3</sup>	DIN 53479
Viscosity			
--	80	Pa·s	
--	80	Pa·s	ISO 3219
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	23		ISO 868
Tensile Strength	1.50	MPa	ISO 37
Tensile Elongation at Break	350	%	ISO 37
Tear Strength	7.00	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT