# Lifoflex® UV FLAM 90700

## Thermoplastic Elastomer

#### Müller Kunststoffe GmbH

#### Message:

Lifoflex® UV FLAM 90700 is a Thermoplastic Elastomer (TPE) material. It is available in Europe for extrusion or injection molding. Important attributes of Lifoflex® UV FLAM 90700 are:

Flame Rated

**RoHS Compliant** 

Flame Retardant

Good Adhesion

Good Flexibility

Typical applications include:

Engineering/Industrial Parts

**Construction Applications** 

Electrical/Electronic Applications

Wire & Cable

General Information					
Features	Flame Retardant				
	Good Adhesion				
	Good Flexibility				
	Good Processability				
	Halogen Free				
	Low Compression Set				
	Low Smoke Emission				
	Low Toxicity				
Uses	Building Materials				
	Cable Jacketing				
	Electrical Parts				
	Gaskets				
	Grommets				
	Profiles				
Agency Ratings	DIN 5510-2:2009-5				
	DIN EN ISO 5659-2				
	EU 2003/11/EC				
RoHS Compliance	RoHS Compliant				
Processing Method	Extrusion				
	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	1.05	g/cm³	ISO 1183/A		

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	90		DIN 53505
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress - Flow (Yield)	6.40	MPa	DIN 53504
Tensile Elongation - Flow (Break)	630	%	DIN 53504
Compression Set			ISO 815
23°C, 72 hr	42	%	
70°C, 22 hr	58	%	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
	850		

Glow Wire Flammability Index (1.60 mm)

650

°C

IEC 60695-2-12

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

