UNISOFT TPE™ ST-40A-BK-3-01

Styrene Ethylene Butylene Styrene Block Copolymer

UNITED SOFT PLASTICS, Inc.

Message:

TPE Compound based on Styrene-Ethylene/Butylene-Styrene Block Copolymer

| General Information | | | |
|------------------------------|------------------------------------|-------|-------------|
| Features | Bondability | | |
| | Good Adhesion | | |
| | | | |
| Uses | Adhesives | | |
| | Automotive Applications | | |
| | Bonding | | |
| | Electrical/Electronic Applications | | |
| | | | |
| Appearance | Black | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| | Injection Molding | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.18 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.80 to 2.7 | % | ASTM D955 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 40 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 5.00 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 750 | % | ASTM D412 |
| Injection | Nominal Value | Unit | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

°C

°C

°C

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

185 to 205

205 to 220

30.0 to 65.0

Tel: +86 21 5895 8519 Phone: +86 13424755533

Front Temperature

Nozzle Temperature

Mold Temperature

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

