

# UNISOFT ADHESION™ AD-66A-NT-1-01

Styrene Ethylene Butylene Styrene Block Copolymer

UNITED SOFT PLASTICS, Inc.

Message:

TPE Compound based on Styrene-Ethylene/Butylene-Styrene Block Copolymer  
Special bonding grade to PC/ABS, PC/PBT, PC, ABS, PBT, PET and PET-G; excellent processing;  
Unisoft Adhesion™ AD-66A-NT-1-01 is a general adhesion grade intended for use in injection molding and extrusion processes. All ingredients used for this compound are in compliance with certain FDA regulations.

General Information	
Features	Block Copolymer
	Workability, good
	Adhesiveness
	Good adhesion
Uses	Adhesive
Agency Ratings	FDA not rated
Appearance	Natural color
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	1.0 - 2.0	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	66		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	5.00	MPa	ASTM D412
Tensile Elongation (Break)	480	%	ASTM D412
Injection	Nominal Value	Unit	
Drying Temperature	65.6	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	199 - 210	°C	
Front Temperature	218 - 229	°C	
Nozzle Temperature	235 - 246	°C	
Mold Temperature	40.6 - 65.6	°C	
Injection instructions			

Temperatures are shown for PET adhesion.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

