

RTP 103 AV (Solid)

Polypropylene

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Foamable		
RoHS Compliance	Contact Manufacturer		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40 to 0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3450	MPa	ASTM D638
Tensile Strength (Yield)	45.5	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	4140	MPa	ASTM D790
Flexural Strength (Yield)	68.9	MPa	ASTM D790
Compressive Strength	48.3	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	43	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	210	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	149	°C	
1.8 MPa, Unannealed	138	°C	
CLTE - Flow	4.5E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.29	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257

Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	2.80		ASTM D150
Dissipation Factor (1 MHz)	1.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	2.0	hr	
Suggested Max Regrind	20	%	
Rear Temperature	204 to 221	°C	
Middle Temperature	210 to 227	°C	
Front Temperature	216 to 232	°C	
Mold Temperature	21.1 to 65.6	°C	
Injection Pressure	34.5 to 68.9	MPa	
Back Pressure	0.345	MPa	
Screw Speed	50 to 90	rpm	
Clamp Tonnage	6.9 to 11	kN/cm ²	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT