

TECHNYL STAR™ AFX 218 V60 BLACK 31N

Polyamide 66
Solvay Engineering Plastics

Message:

TECHNYLSTAR™ AFX 218 V60 Black 31 N is based on a patented high flow polyamide 66 resin (Technylstar), heat stabilized, reinforced with 60% of glass fibre, for injection moulding. It is available in black color.

General Information				
Filler / Reinforcement		Glass Fiber,60% Filler by Weight		
Additive		Heat Stabilizer		
Features		Good Surface Finish		
		Heat Stabilized		
		High Flow		
Agency Ratings		UU 453/2010/EC		
RoHS Compliance		RoHS Compliant		
Appearance		Black		
Processing Method		Injection Molding		
Part Marking Code (ISO 11469)		>PA66-GF60<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.69	--	g/cm ³	ISO 1183/A
Molding Shrinkage				Internal Method
Across Flow	0.39	--	%	
Flow	0.32	--	%	
Water Absorption (23°C, 24 hr)	0.60	--	%	ISO 62
Molding Shrinkage Isotropy	0.820	--		Internal Method
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	22000	18000	MPa	ISO 527-2/1A
Tensile Stress (Break)	268	195	MPa	ISO 527-2/1A
Tensile Strain (Break)	2.1	3.1	%	ISO 527-2/1A
Flexural Modulus	19000	--	MPa	ISO 178
Flexural Stress	416	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	22	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	98	100	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	18	21	kJ/m ²	ISO 180/1A

Unnotched Izod Impact Strength	85	93	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	257	--	°C	ISO 75-2/Af
Melting Temperature	264	--	°C	ISO 11357-3
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	260 to 270		°C	
Middle Temperature	270 to 280		°C	
Front Temperature	280 to 290		°C	
Mold Temperature	60.0 to 90.0		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

