Manner Flexible PVC V971

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

Message:

Recommended Applications: Lead-free 75°C jacket compound with excellent low temperature properties. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

| General Information | | | |
|-------------------------------------------------------------------|----------------------------|-------|----------------|
| Features | Low (to None) Lead Content | | |
| Uses | Cable Jacketing | | |
| | Wire & Cable Applications | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.35 to 1.39 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness | | | ASTM D2240 |
| Shore A | 83 to 89 | | |
| Shore A, 15 sec | 77 to 83 | | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus - 100% Secant ¹ | 8.96 | MPa | ASTM D638 |
| Tensile Strength ² | 16.5 | MPa | ASTM D638 |
| Tensile Elongation ³ (Break) | 300 | % | ASTM D638 |
| Aging | Nominal Value | Unit | Test Method |
| Change in Tensile Strength in Air ⁴ (100°C, 240 hr) | 10 | % | UL Unspecified |
| Change in Ultimate Elongation in Air ⁵ (100°C, 240 hr) | -7.0 | % | UL Unspecified |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -48.0 | °C | ASTM D746 |
| Flammability | Nominal Value | Unit | Test Method |
| Oxygen Index | 31 | % | ASTM D2863 |
| NOTE | | | |
| 1. | Unaged Dumbbells: .03 inch | | |
| 2. | Unaged Dumbbells: .03 inch | | |
| 3. | Unaged Dumbbells: .03 inch | | |
| 4. | Air Retention: .03 inch | | |
| 5. | Air Retention: .03 inch | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

