

Borealis PP HL708FB

Polypropylene Homopolymer

Borealis AG

Message:

HL708FB is a polypropylene homopolymer intended for fibre applications

General Information			
Features	Controlled Rheology		
	Good Processability		
	High Flow		
	Homopolymer		
Uses	Fibers		
	Meltblown Nonwovens		
Processing Method	Meltblown Nonwovens		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	800	g/10 min	ISO 1133
Molecular Weight Distribution	Very narrow		
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	158	°C	ISO 11357

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT