## Dow Corning® QP1-50

## Silicone

## Dow Corning Corporation

## Message:

Translucent, Uncatalyzed Silicone Rubber Base

APPLICATIONS

Dow Corning® QP1 Silicone Elastomer Bases are an uncatalyzed material designed for compounding into elastomer used for part fabrication of medical devices and device components including those intended for implantation in humans for less than 30 days and non-implant applications. DESCRIPTION

Dow Corning QP1 Silicone Elastomers are a one-part high consistency rubber base which is supplied absent any catalyst. Once compounded with peroxide it can be used to fabricate parts by extrusion, calendaring or molding. When compounded and cured as indicated, the resulting elastomer consists of cross-linked dimethyl and methyl-vinyl siloxane copolymers and reinforcing silica.

General Information	
Features	Good coloring
Uses	Medical/nursing supplies
Agency Ratings	USP Class VI
Appearance	Translucent
Processing Method	Extrusion
	Calendering
	Injection molding

Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.13	g/cm³	ASTM D792	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	49		ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress (200% Strain)	2.40	MPa	ASTM D412	
Tensile Strength	11.8	MPa	ASTM D412	
Tensile Elongation (Break)	550	%	ASTM D412	
Tear Strength <sup>1</sup>	18.0	kN/m	ASTM D624	
Compression Set (177°C, 22 hr)	43	%	ASTM D395	
Additional Information				
Values taken from samples made with Perkadox PD-50S.				
NOTE				

1.

B mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

