

QAMAR FC21HS

Linear Low Density Polyethylene
SPDC Ltd.

Message:

QAMAR FC21HS is a linear low density polyethylene material. This product is available in North America, Africa and the Middle East, Europe or Asia Pacific region. The processing method is blow molded film.
The main features of QAMAR FC21HS are:
Antiblock software
slide
Transparency
The typical application fields of QAMAR FC21HS are: movies

General Information			
Additive	Anti-caking agent		
	slip agent		
Features	smoothness		
	Anti-caking property		
	Definition, high		
	General		
Uses	Films		
	General		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)	1.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	55		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			JIS K6760
Yield	12.0	MPa	JIS K6760
Fracture	32.0	MPa	JIS K6760
Tensile Strain (Break)	900	%	JIS K6760
Apparent Bending Modulus	260	MPa	ASTM D747
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	30	µm	
Tensile Modulus			ISO IR 1184
MD : 30 µm	190	MPa	ISO IR 1184
TD : 30 µm	220	MPa	ISO IR 1184

Tensile Stress			JIS Z1702
MD: Break, 30 μm	55.0	MPa	JIS Z1702
TD: Break, 30 μm	40.0	MPa	JIS Z1702
Tensile Elongation			JIS Z1702
MD: Break, 30 μm	550	%	JIS Z1702
TD: Break, 30 μm	850	%	JIS Z1702
Dart Drop Impact (30 μm)	120	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD : 30 μm	30	g	ASTM D1922
TD : 30 μm	160	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	102	°C	ASTM D1525
Melting Temperature	122	°C	DSC
Optical	Nominal Value	Unit	Test Method
Haze (30.0 μm)	9.0	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	190 - 210	°C	
Melt Temperature (Aim)	200	°C	
Extrusion instructions			

Blow up Ratio: 2 to 4Screw Type: LLDPE ScrewDie Lip Gap: 2.0 to 3.0 mmAir Ring: Single or Dual Slit (Wide die)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT